

TECHNICAL DATA SHEET

DIMENSIONS

FORMAT

Length	2050mm
Width	240mm
Number of panels per pack	7
m ² per pack	3,444
Bevels	4V pressed bevel
Thickness	8 mm
Tongue and groove	Uniclic
Water resistant	No

FACTORY WARRANTY

	METHOD	PARAMETERS	VALUES	
Usage class	EN ISO 10874		Class	21-22-23/31-32
CE	EN 14041:2004 / AC:2006	Notified body	NB 0493 - Centexbel	DOP : On pack
UKCA	EN 14041:2004 / AC:2006	Approved body	AB 8515 - Centexbel	DOP : On pack
	Residential use	See warranty conditions		
Warranty	Commercial use	See warranty conditions		
	Water resistancy	See warranty conditions		

GENERAL DATA (ACCORDING TO EN 13329)

	METHOD	PARAMETERS	NORM REQUIREMENTS	VALUES
Abrasion resistance	ISO24338 - Procedure A		≥ 4000 cycles	≥ 4000 cycles
Abrasion class	EN 13329		AC4	AC4
Impact resistance	EN 17368	Small ball	≥ 35mm	≥ 35mm
	EN 13329	Big ball	≥ 600mm	≥ 600mm
Scratch resistance	EN 438-2, 25		Charge ≥ 3N	Charge ≥ 3N
Effect of a castor chair	ISO 4918 (with underlay)	Type W (EN 12529)	15000 cycles	No change
Thickness swelling	ISO 24336	After 24h immersion at 20°C	≤ 18%	≤ 18%
Locking strength	ISO 24334	F10,2 long side	≥ 1 kN/m	≥ 1 kN/m
		Fmax long side		≥ 1 kN/m
		Fs0,2 short side	≥ 2 kN/m	≥ 2 kN/m
		Fmax short side		≥ 2 kN/m
Effect of a furniture leg	EN 424		No damage shall be visible, when tested with foot type 0	No visible damage
Resistance to staining	EN 438	Group 1,2 Group 3	Class 5 Class 4	Class 5 Class 4
Light fastness	EN ISO 4892 2:2006/A1:2009 Procedure B - Cycle 5	Grey reference	Class ≥ 4	Class 4

ENVIRONMENT, SAFETY & HEALTH

	METHOD	PARAMETERS	NORM REQUIREMENTS	VALUES
Formaldehyde emission	EN 717-1	ppm	E1	< 0,5
Anti-static	EN 1815		≤ 2,0 kV	≤ 2,0 kV
Reaction to fire	EN 13501-1	Class		Cfl-s1
Thermal resistance	EN 12667	m ² K/W		0,055 m ² K/W
Slip resistance	EN 13893	μ	μ ≥ 0,30	DS: μ ≥ 0,30



EN 14041:2004 / AC:2006
Centexbel Floorcoverings
EN 13329:2018

EN 14041:2004 / AC:2006
Centexbel Floorcoverings
EN 13329:2018